

Aquaproof 2K

Flexible acrylic cement modified waterproof coating

DESCRIPTION

Aquaproof 2K is a two component polymer modified cementitious, flexible waterproof coating for internal and external applications available in many attractive colours.

APPLICATIONS

- » For waterproofing of water retaining structures and reservoirs.
- » To provide protection for concrete substrates and masonry against carbon dioxide, chloride ions, water and de-icing salts.

ADVANTAGES

- » Waterproof, suitable for water retaining structure and basements.
- » Breathable, water vapour preamble.
- » Durable, excellent resistance to UV attack.
- » Excellent protection against carbon dioxide, chloride ions and water.
- » Non-toxic, suitable for drinking water.
- » Cost effective, quick and easy brush or spray application.
- » Suitable for internal and external applications.

STANDARDS

Aquaproof 2K complies with:

- » EN 14891 CMO1P.
- » EN 1502-2 Principle 1(PI); 2(MC); 8(IR).

METHOD OF USE

SUBSTRATE PREPARATION

The surfaces to be coated should be clean, sound, and free from contamination. Remove any traces of curing compound, laitance, mold release agents, organic growth, or any other loose materials. This is best obtained by using high pressure water or light grit blasting.

Honey combing, damaged or deteriorated concrete exists, the substrate should be repaired using suitable low permeability repair mortar from DCP repair systems before commencing the coating.

Note: Solvent based primers and coatings like Repcoat primer and Setseal A should be removed mechanically before applying Aquaproof 2K.

TECHNICAL PROPERTIES:

Colour:	Grey
Density:	1.90 ± 0.10 g/cm ³
Water permeability at positive pressure: DIN 1048-5	Impermeable @ 3 bars, 3 days
Water permeability at negative pressure: DIN 1048-5	Impermeable @ 1.5 bars, 3 days

TECHNICAL PROPERTIES EN 1504-2:

Adhesion to concrete:	1.46 N/mm ²
Static crack-bridging at -10°C:	Class A2 > 0.25 mm
Static crack-bridging at -20°C:	Class A1 > 0.1 mm
Resistance to thermal shock @ 70°C:	≥ 1.5 N/mm ²
Capillary absorption and permeability to water:	< 0.1 kg/m ² .h ^{0.5}
Permeability to water vapour - equivalent thickness of air S _D :	Class 1: SD < 5 m (Vapour Permeability)
Permeability to Carbon Dioxide (CO ₂):	> 50 m
Chloride ions content:	0.05%

Aquaproof 2K

PRIMING

No primer is required, but substrates should be pre-soaked with clean water prior to application of Aquaproof 2K.

MIXING

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used. The 5 kg of Aquaproof 2K liquid should be added to a clean container.

The 15 kg powder is then added slowly to the liquid while mixing continuously with low speed mixer/drill (400 - 600 rpm). Mixing time should be continued for 3 minutes until a uniform consistency is obtained.

APPLICATION

Aquaproof 2K can be applied by brush or spray. The mixed material should be brushed well into the surface. Strike off with the brush in one direction.

Care must be taken not to spread the material too thin. When the material begins to drag, do not add any water, but dampen the surface again.

Leave the first coat to cure for a minimum 4 hours before applying the second coat, depending on ambient temperature, relative humidity and ventilation conditions. If the first coat is left for more than one day or if it is very dry, pre-soaking with clean water is needed before applying the second coat.

The second coat shall be applied by brush in a similar way to the first layer but preferably perpendicular to the previous layer to ensure good bond and coverage. Tiling over the waterproofing could start after a minimum of 4 hours after the application of the second layer, depending on ambient temperature, relative humidity and ventilation conditions.

CLEANING

All tools should be cleaned immediately after finishing by clean water. Hardened materials should be cleaned mechanically.

TECHNICAL PROPERTIES EN 14891:

Initial tensile adhesion strength after aging under standard conditions:	≥ 0.5 N/mm ²
Adhesion strength after immersion in water:	≥ 0.5 N/mm ²
Tensile adhesion strength after freeze-thaw cycles:	≥ 0.5 N/mm ²
Tensile adhesion strength after heat ageing @ 70°C:	≥ 0.5 N/mm ²
Tensile adhesion strength after contact with lime water:	≥ 0.5 N/mm ²
Tensile adhesion strength after contact with chlorinated water:	> 0.5 N/mm ²
Permeability @ 150 kPa:	Nil
Crack bridging ability under standard conditions at 20°C and 50% RH:	> 0.75 mm
Crack bridging ability at low temperature @ - 5°C:	> 0.75 mm

REMARKS

- » Aquaproof 2K should not be applied to frozen substrate or if ambient temperature is below 5°C or expected to fall below 5°C.
- » Fair faced concrete should be roughened mechanically to ensure good adhesion, if this is not possible contact DCP technical department for advice.

PACKAGING

Aquaproof 2K is available as 20 kg packs (5.1 kg polymer & 14.9 kg powder).

COVERAGE

Approximately 11 m²/20 kg for one coat @ 1 mm thickness.

Don Construction Products Bulgaria EAD

Tsvetan Lazarov 152
Techno Park, Sofia 1582
Bulgaria
info.bulgaria@dcp-int.com
www.dcp.bg

Aquaproof 2K

STORAGE

Aquaproof 2K has a shelf life of 12 months from date of manufacture if stored at temperatures between 5°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advise.

CAUTIONS

HEALTH AND SAFETY

As Aquaproof 2K contains Portland cement and sand, Aquaproof 2K may cause irritation to skin or eyes. In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advise.

For further information refer to the Material Safety Data Sheet.

FIRE

Aquaproof 2K is nonflammable.

Don Construction Products Bulgaria EAD

Tsvetan Lazarov 152
Techno Park, Sofia 1582
Bulgaria
info.bulgaria@dcp-int.com
www.dcp.bg



Aquaproof 2K

MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

Don Construction Products Bulgaria EAD

Tsvetan Lazarov 152
Techno Park, Sofia 1582
Bulgaria
info.bulgaria@dcp-int.com
www.dcp.bg

Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

www.dcp-int.com

DCP Building Excellence



08-0088-BG-B-2024