

# Cemafill RTL

Multipurpose cementitious tile grout



## Description

Cemafill RTL is a multipurpose cementitious tile grout for interior and exterior applications with all types of ceramic tiles such as single glazed, double glazed and porcelain in dry or wet conditions for joint widths up to 6 mm.

The high abrasion resistant properties of Cemafill RTL make it suitable for grouting floor and wall joints in residential and commercial buildings. Cemafill RTL is available in wide range of brilliant colours that provide a uniform and aesthetic joint appearance.

## Applications

- ▲ Grouting all types of ceramic tiles and natural stones up to 6 mm.
- ▲ Suitable for indoor and outdoor areas.
- ▲ Suitable for floor and wall applications.
- ▲ Suitable for bathrooms, kitchens and other wet areas.

## Advantages

- ▲ High abrasion resistance.
- ▲ Reduced water absorption properties, suitable for wet areas.
- ▲ Improved hygienic properties, anti-mould and stain resistance.
- ▲ Low shrinkage rate, free of cracks.
- ▲ Uniform colour, for aesthetic joint appearance.
- ▲ Easy to apply, non-sag with good workability.
- ▲ Available in wide range of brilliant colours.

## Limitations

Do not use for:

- ▲ Joint widths exceeding 6 mm.
- ▲ Grouting tiles in industrial floors where high chemical resistance is required.
- ▲ Cases where a rapid utilization of surfaces is required.
- ▲ Filling expansion, contraction or construction joints in walls and floors. These joints should be filled with a suitable flexible sealant from the DCP Flexseal range.

## Technical Properties @ 23 ± 2°C. W/P = 0.34:

Fresh wet density:	1.75 ± 0.10 g/cm <sup>3</sup>
Working time:	70 - 90 min
Compressive strength: ISO 13007-4, 4.1.4	> 15 MPa @ 28 days
Flexural strength: ISO 13007-4, 4.1.3	> 2.5 MPa @ 28 days
Shrinkage: ISO 13007-4,4.3	< 3.0 mm/m
Abrasion resistance: ISO 13007-4,4.4	< 1000 mm <sup>3</sup>
Water absorption: ISO 13007-4,4.2	< 5 g @ 240 min
VOC: ASTM D2369	< 10 g/ltr (complies with LEED)

## Standards

Cemafill RTL complies with the following standards:

- ▲ ISO 13007-3 and BS EN 13888 as an improved cementitious grout with additional characteristics of reduced water absorption and high abrasion resistance (CG2AW).
- ▲ ANSI A118.6 as a standard cementitious grout.

## Method of Use

### Substrate Preparation

Before grouting, ensure that the adhesive has completely dried and hardened. Adhesive should be left for 24 hours before applying the grout, unless rapid setting adhesives is used.

All tiles and joints must be clean and free from oil, grease or loose materials.

Remove the tile spacers and ensure that the grout joints are uniform and their width does not exceed 6 mm to avoid slumping.

**Don Construction Products Qatar W.L.L**  
New Industrial Area, Street 21,  
Zone 81, bldg. # 9  
Doha - Qatar



# Cemafill RTL

## Mixing

To ensure proper mixing, a mechanically powered mixer or drill fitted with suitable paddle should be used.

1.65 - 1.75 litres of clean fresh water for each 5 kg bag (water/powder ratio of 0.33 - 0.35 by weight) should be added to a clean container. The powder is then added slowly to the water while mixing continuously at low speed (400 - 600 rpm).

Mixing time should be continued for 3 minutes until a uniform consistency and free of lumps mixture is obtained. Allow a slake time for 5 minutes, then remix for additional 1 minute without adding any more water.

*Important: Adding too much water will weaken the joints, cause surface discoloration, and promote the formation of cracks, always follow the mentioned mixing ratio.*

## Application

- ▲ Using appropriate spatula or rubber float, fill with pressure the joints completely with Cemafill RTL.
- ▲ Immediately, remove the excess grout by moving the spatula or the edge of the rubber float diagonally to the tiles.
- ▲ When the grout starts to set (usually 20 - 30 minutes at normal conditions), use a damped sponge in a circular motion to remove the excess grout and level the joints.
- ▲ After drying, clean the tiles surface using a dry cloth.

It is recommended to remove grout from the tile surfaces before full setting of the grout. Failure to do so may result in difficulty in removing any remains and makes it necessary to use a mechanical means in cleaning, which may scratch the tile surfaces.

## Cleaning

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleaned mechanically.

## Packaging

Cemafill RTL is available in 5 kg bags.

## Yield

The approximate yield of the grout can be calculated as per the following equation:

$$\text{Yield (m}^2\text{/kg)} = \frac{6}{\text{WD} \left(0.02 + \frac{1}{L} + \frac{1}{H}\right)}$$

Where:

L: Tile length (cm)

H: Tile width (cm)

D: Average joint depth (mm)

W: Average joint width (mm)

*Note: Grout yield subject to ±15% tolerance.*

## Storage

Cemafill RTL has a shelf life of 12 months from date of manufacture if stored at temperatures between 2°C and 50°C.

If these conditions are exceeded, DCP Technical Department should be contacted for advice.

## Cautions

### Health and Safety

As Cemafill RTL contains Portland cement, Cemafill RTL may cause irritation to skin or eyes.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice if necessary.

For further information refer to the Material Safety Data Sheet.

### Fire

Cemafill RTL is nonflammable.

**Don Construction Products Qatar W.L.L**  
New Industrial Area, Street 21,  
Zone 81, bldg. # 9  
Doha - Qatar

## More from Don Construction Products

A wide range of construction chemical products are manufactured by DCP which include:

- ▲ Concrete admixtures.
- ▲ Surface treatments
- ▲ Grouts and anchors.
- ▲ Concrete repair.
- ▲ Flooring systems.
- ▲ Protective coatings.
- ▲ Sealants.
- ▲ Waterproofing.
- ▲ Adhesives.
- ▲ Tile adhesives and grouts.
- ▲ Building products.
- ▲ Structural strengthening.

**Don Construction Products Qatar W.L.L**  
New Industrial Area, Street 21,  
Zone 81, bldg. # 9  
Doha - Qatar

# Cemafill RTL

**Don Construction Products Qatar W.L.L**  
New Industrial Area, Street 21,  
Zone 81, bldg. # 9  
Doha - Qatar

**Note:**

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

-  expertise
-  quality
-  full range

[www.dcp-int.com](http://www.dcp-int.com)



10-0044-A-2020