

# Cemflow Topping Pigmented

Coloured industrial grade floor topping (apple, sky, almond, chalk, sand)



## DESCRIPTION

Cemflow Topping Pigmented is a self-smoothing, dimensionally stable, and fast drying industrial grade floor topping designed for upgrading and renovating new and existing internal floors.

Cemflow Topping Pigmented is supplied as a pre-blended dry powder designed for application between 5 mm to 15 mm (in one application) to provide a finished industrial floor.

Typically, Cemflow Topping Pigmented can be pumped up to 1500 m<sup>2</sup> per day. Coverage of 600 m<sup>2</sup> can be achieved when hand applied, dependent upon manpower and equipment used.

Cemflow Topping Pigmented is recommend to be sealed with Cemflow Sealer. (Further information is available from our Technical Department or the Product Data Sheets).

Cemflow Topping Pigmented is also protein free so may be used in biologically sensitive areas.

## APPLICATIONS

Cemflow Topping Pigmented is suitable for use in a wide range of industrial and commercial environments such as schools, showrooms, galleries, hospitals, factories, warehouses etc. subjected to medium to heavy traffic. It is suitable for application onto a wide range of subfloor types, including; sand and cement screeds, concrete, terrazzo, granolithic, epoxy and polyurethane resins and waterproof membranes.

## ADVANTAGES

- › Single component, requires only addition of water.
- › Fast setting.
- › Easy and fast application.
- › Excellent adhesion.
- › Excellent abrasion resistance.
- › High coverage efficiency.
- › Highly decorative screed.

## METHOD OF USE

### SUBSTRATE PREPARATION

Concrete and sand/cement screeds must be sound, dry and fully cured (not subject to shrinkage) and any laitance or surface treatments must be removed by mechanical means such as grit blasting. The surface tensile strength of the substrate should be a minimum 1.5 N/mm<sup>2</sup>.

## TECHNICAL PROPERTIES:

Working time:	20 - 30 min @ 20°C
Setting time:	90 min @ 20°C
Foot traffic	3 hr
Light traffic:	24 hr
Heavy traffic:	3 days
Compressive strength: EN 13892-2	> 20 N/mm <sup>2</sup> @ 1 day > 30 N/mm <sup>2</sup> @ 7 days > 35 N/mm <sup>2</sup> @ 28 days
Flexural strength: EN 13892-2	> 4 N/mm <sup>2</sup> @ 1 day > 7 N/mm <sup>2</sup> @ 7 days > 10 N/mm <sup>2</sup> @ 28 days
Abrasion resistance: EN 13892-4	AR0.5 (special)
Slip resistance: EN 13036-4	Dry 78 Wet 60
Flow properties using 30 mm ø x 50 mm flow ring: EN 12706	110 – 130 mm
Consumption per mm thickness:	1.65 kg/ m <sup>2</sup>
Application thickness:	5 – 15 mm

For uneven surfaces, apply Cemflow Base/Renovation to a minimum 5 mm to provide a smooth level surface, prior to the application of Cemflow Topping Pigmented. (Please refer to relevant product Technical Data Sheets).

The concrete substrate should be below 75% RH alternatively Strongcoat DPM should be applied. The temperature of the floor must be maintained above 10°C throughout the application and drying of the Cemflow Topping Pigmented.

## Don Construction Products Ltd.

Helions Bumpstead Road, Haverhill CB9  
United Kingdom  
[info.uk@dcp-int.com](mailto:info.uk@dcp-int.com); [info@dcp-int.co.uk](mailto:info@dcp-int.co.uk)  
[www.dcp-int.com](http://www.dcp-int.com)

# Cemflow Topping Pigmented

## SURFACE PREPARATION

Prior to application on to impervious surfaces the area should be thoroughly cleaned and lightly scarified. Any existing surfaces should be well bonded ( $> 1.5 \text{ N/mm}^2$ ).

The perimeter of the room and any columns should be isolated using a compressible strip. For application over underfloor heating please contact DCP Technical Department for specific advice.

## PRIMING

### TO CONCRETE AND CEMENT SCREEDS

For application onto sand/cement screeds, concrete and other porous substrates, first seal the prepared surface by applying one coat of Cemflow Primer diluted with 3 parts potable water and allow to dry.

Apply a second coat of primer diluted 3:1 by the same method and allow thoroughly to dry. Depending on the porosity of the substrate a further coat may be required.

To confirm if this is necessary a small application area should be undertaken to ascertain the correct priming requirements. As an alternative, Strongcoat Primer may be used.

### PRIMING WITH STRONGCOAT PRIMER

Apply one coat Strongcoat Primer and allow to cure. Apply 2<sup>nd</sup> coat and whilst still tack fully blind with DCP Aggregate at approximately  $3 \text{ kg/m}^2$  until the surface is covered and no resin spots remain. The rate of application is approximately  $3 \text{ kg/m}^2$ .

Allow to dry fully overnight and remove excess aggregate before applying the Cemflow Topping Pigmented.

### TO IMPERVIOUS SURFACES

For application on to impervious surfaces, such as tiles, coatings or onto Strongcoat DPM (please read relevant product technical data sheet).

Apply Strongcoat Primer and whilst it is still tacky fully blind with DCP Coarse Aggregate at approximately  $3 \text{ kg/m}^2$ , until the surface is covered and no resin spots remain. Allow to dry fully overnight and remove excess aggregate before applying the Cemflow Topping Pigmented.

## MIXING

### HAND APPLICATION

Use a power-whisk fitted in a heavy-duty slow speed electric drill. Mix in the proportion of 20 kg of powder to 3.8 – 4.2 litres of potable water. Pour the water into a suitably sized bucket and gradually add the powder while stirring, until a smooth, lump free consistency is achieved.

The material should be mixed for a minimum of 3 minutes. Leave to stand for 2 - 3 minutes and mix briefly for 1 minute before applying.

### PUMP APPLICATION

Mix the powder and water according to the method recommended by the pump manufacturers. In the case of pumps having a continuous water feed adjust the rate of water flow until the mix is a smooth fluid, uniform grey liquid with no surface separation, producing a flow of approximately 130 mm using a 35cc flow ring.

## APPLICATION

Pour or pump the mixed material onto the prepared surface and allow to attain a smooth finish. The use of a spiked roller will help eliminate entrapped air and smooth out flow lines. Apply at a thickness between 5 mm to 15 mm in one pass only.

We would recommend the first coat of Cemflow Sealer should be applied over the Cemflow Topping Pigmented a minimum of 6 hours after application. (Please refer to Cemflow Sealer Technical Data Sheet).

## CLEANING

Wash tools with water immediately after use.

## PRECAUTIONS

- » Do not place when the substrate temperature is below  $10^\circ\text{C}$  or when the ambient temperature is  $10^\circ\text{C}$  and falling.
- » Protect from frost.
- » Do not exceed the maximum recommended water content and only use potable cold water.
- » This product is not recommended for external use or situations where water may come into direct contact with the cured material.
- » This product should not be applied to asphalt or bituminous surfaces.



# Cemflow Topping Pigmented

## **PACKAGING**

Cemflow Topping Pigmented is available in 20 kg paper sacks.

## **COVERAGE**

A 20 kg bag using 4.00 litres of clean water will yield approximately 12 litres.

A 20 kg pack of Cemflow Topping Pigmented will cover approximately 2.4 m<sup>2</sup> at 5 mm thickness

## **STORAGE**

Protect from frost and store under dry warehouse conditions at a temperature between 10°C and 30°C.

## **SHELF LIFE**

6 months in unopened bags and stored under good conditions.

## **HEALTH AND SAFETY**

Consult the appropriate Material Safety Data Sheet prior to using each product.



# Cemflow Topping Pigmented

## MORE FROM DON CONSTRUCTION PRODUCTS

A wide range of construction chemical products are manufactured by DCP which include:

- » Concrete admixtures.
- » Surface treatments
- » Grouts and anchors.
- » Concrete repair.
- » Flooring systems.
- » Protective coatings.
- » Sealants.
- » Waterproofing.
- » Adhesives.
- » Tile adhesives and grouts.
- » Building products.
- » Structural strengthening.

### **Don Construction Products Ltd.**

Helions Bumpstead Road, Haverhill CB9  
United Kingdom  
[info.uk@dcp-int.com](mailto:info.uk@dcp-int.com); [info@dcp-int.co.uk](mailto:info@dcp-int.co.uk)  
[www.dcp-int.com](http://www.dcp-int.com)

**Note:**

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

[www.dcp-int.com](http://www.dcp-int.com)

DCP Building Excellence