

# STRONGCOAT DPM

Epoxy damp-proof membrane



TECHNICAL DATA SHEET PUBLISHED JUNE 2014

## PRODUCT FEATURES

**Strongcoat DPM** is a two-pack, solvent free epoxy-based damp-proof membrane for use with the DCP range of surface coatings and toppings. It suppresses residual construction moisture and rising dampness in concrete and sand/cement screeds and can be used in situations where the relative humidity level is above 75%. It is applied by brush or roller in one or two coats depending on the relative humidity of the floor.

## KIT FORM

10 and 5Kg

## SPECIFIED COATING THICKNESS

Approximately 200 microns per coat.

## COVERAGE

On grit blasted and textured surfaces, approximately 3.5m<sup>2</sup> per Kg for the first coat and up to 5m<sup>2</sup> per Kg for the second coat. Coverage figures will vary according to the texture, porosity and evenness of the surface on which the Strongcoat DPM is being applied.

## STORAGE

Store at temperatures between 5°C and 30°C.

## SHELF LIFE

Approximately 12 months if stored in unopened containers and under good conditions.

## SURFACE PREPARATION

The surface must be clean, dry and free from dust, laitance, oils, paints or other forms of contamination. Grit blasting can be used to remove laitance and surface contamination (see the DCP Guide to Surface Preparation for further details). For treatment of surfaces containing expansion joints consult our Technical Department.

## NUMBER OF COATS REQUIRED

One coat of Strongcoat DPM is required where the relative humidity level of the screed is between 75% and 85%. For RH levels between 86% and 98%, use 2 coats.

## TECHNICAL INFORMATION

EN 1318 Designation	SR-B2,0
Bond Strength (EN 13892-8)	≥ 2.0 N/mm <sup>2</sup>

## MIXING

Taking care to ensure that the bottom and sides are thoroughly scraped, transfer the entire contents of the Strongcoat DPM Hardener container into the Resin container and, using a Jiffytype mixer attached to a slow-running electric drill, mix for approximately two minutes.

**Never mix Strongcoat DPM by hand as this could lead to areas of uncured material.**

## APPLICATION

Once mixing is complete, transfer the Strongcoat DPM to a roller tray and, using a medium-pile simulated sheepskin roller, apply it evenly over the surface.

## WORKING TIME

Strongcoat DPM has a working time of approximately 20 minutes at 20°C.

- **Never leave the mixed Strongcoat DPM kit to stand for any length of time prior to application as this will considerably shorten its working time.**

## CLEANING

Once mixing and application are complete, tools can be cleaned with a suitable solvent. Cured material can only be removed mechanically.

## CURING TIME

At 20°C, Strongcoat DPM should be allowed to cure for 18 hours prior to carrying out further operations on it. At lower temperatures the cure time will be extended (consult our Technical Department for details of curing times at other temperatures).



## OVERCOATING

The second coat of Strongcoat DPM must be applied no later than 24 hours after the first coat has cured (see Curing Time).

The first coat must not be contaminated prior to applying the second coat.

## WORKING CONDITIONS

Strongcoat DPM should not be applied / cured at temperatures less than 10°C.

## HEALTH & SAFETY

Consult the appropriate Material Safety Data Sheets prior to using Strongcoat DPM.

## GENERAL GUIDANCE

This data sheet is for general purposes only and may contain information which is inappropriate for certain conditions of use. Accordingly, all recommendations and suggestions are made without guarantee. Further information is available from our Technical Department.

Don Construction Products Ltd Hawthorn House, Helions Bumpstead Road,  
Haverhill, Suffolk CB9 7AA, UK T: +44 (0) 1440 766360

### Note:

We endeavour to ensure that any information, advice or recommendation we may give in product literature is accurate and correct. However, because we have no control over where and how products are applied, we cannot accept any liability arising from the use of the products.

[www.dcp-int.com](http://www.dcp-int.com)

 expertise

 quality

 full range